

Product Data Sheet

950-(6)-02/18



Makers of Fine Paint Since 1962

ISSUED: 12 February 2018

Page 1 of 2

950 Flexicoat

USE



THINNER/CLEAN



T-80
T-14

APPLICATION



RE-COAT



4 Hrs

HAZARD



OTHER

Fast drying, solvent based coating with highly elastic properties.

USES: On metal and other substrates where a coating with rubber like ie extremely flexible properties is required. The high flexibility of this coating makes it an excellent coating for foam rubber and urethane foams.

SURFACE PREPARATION: All surfaces should be clean, dry and free from oil and grease. Use 129 Super Etch Primer on bright and non ferrous surfaces. Steel surfaces should be primed with suitable anti corrosive primers such as 131 Superbond or 291 Satin Primer systems. On timber use 307 White Wood Undercoat. Where maximum flexibility (ie flexible substrates) is required the use of primers is not recommended.

APPLICATION: Stir thoroughly until product is uniform. Product may be applied using roller or airless spray.

THINNING: Approximately 20% with T-80 Reducer. In hot conditions the addition of some T-18 Reducer is recommended to slow down the drying time thus preventing dry spray.

CLEAN UP: T-80 Reducer or T-14 Gunwash.

DRYING: Touch dry in 10 minutes, hard dry after overnight at 25°C. May be re-coated within 4 hours of application or after 24 hours.

COLOUR: White. A range of special colours available - minimum quantity will vary with the colour.

FINISH: Satin.

COVERAGE: Theoretical coverage 8 m²/Litre at 50 microns dry film thickness.

PACK SIZES: 20 Litre.

VEHICLE TYPE: Modified polymer resins.

PIGMENT TYPE:

Lightfast pigment appropriate for that colour.

FILM PROPERTIES:

Solvent Resistance	Fair.	Chemical Resistance	Good.
Abrasion Resistance	Good.	Impact Resistance	Good.
Heat Resistance	Up to 100°C. White and pastel will show some yellowing at higher temperatures.	Flexibility	Excellent.

TOPLINE PAINT PTY LTD

Telephone: (08) 8384 1188

33 ALDERSHOT ROAD, LONSDALE, SOUTH AUSTRALIA 5160.

Fax: (08) 8326 1824

E-mail: admin@toplinepaint.com.au

Customers need to appreciate that as Topline Paint cannot control the conditions under which our products are used, we therefore are unable to guarantee suitability or accuracy in every situation. If any doubt exists, do check with our technical people. Before large-scale use always test on a small sample and ascertain suitability. No warranties express or implied are made. The risks and liability arising from handling, storage, use and compliance with legal restrictions, rests with the buyer.





950 Flexicoat

PRECAUTIONS:

The following information is a general guide only. Industrial users (ie where the product is being used in the workplace) are legally required to have available a Safety Data Sheet on this product. If you are unsure if you have an SDS on this product please contact Topline Paint and one will be provided.

Safety Directions: **KEEP OUT OF REACH OF CHILDREN – DO NOT SWALLOW.** Breathing the vapour is harmful and may cause lung irritation. Avoid contact with skin and eyes. Wear suitable, protective clothing, eye protection and impervious gloves when mixing and using. Handling and usage of this product must be carried out under well ventilation conditions that prevent inhalation of vapours, dust or mist. Use the appropriate breathing equipment (refer to Aust Stand. 1716) when ventilation is restricted. Keep containers closed when not in use. Eliminate any source of ignition (open fires, pilot lights, furnaces, spark producing switches etc.) as this product is flammable. **DO NOT SMOKE.** Take precautionary measures against static discharges. Used clean up rags may spontaneously ignite. To avoid ignition immerse in water or store in a sealable glass container.

First Aid Instructions: If affected by inhalation, remove to fresh air. If breathing difficulty persists or occurs later, consult a doctor. If swallowed, **DO NOT INDUCE VOMITING** drink plenty of water and seek medical advice. Contact a Doctor of Poisons Information Centre (Phone 131126). If skin contact occurs, remove contaminated clothing and wash skin thoroughly with soap and water. If irritation occurs seek prompt medical advice. Immerse contaminated clothing in water for 24 hours and do not use until laundered. In case of eye contact, hold eyes open and flood with running water for at least 15 minutes seek medical advice.

Leaks, Spills and Disposal: To prevent ignition of fumes product shut off all ignition sources. Contain or shut off leak if safe to do so. For large leaks or spills of volatile, flammable product, use respiratory protection, protective apparel and footwear. Spills should be absorbed either with rags (small spill) or dry sand/earth (large spill). In the case of flammable product spillage, use spark free implements to place rags or absorbed material into a solvent resistant container. Cover with water for 24 hours before disposal. DO NOT pour left over product down the drain – retain it in marked sealed container for future use or disposal through chemical waste collection programs. Dried empty cans can be recycled and should be disposed of via council steel recycling facilities.

Fire: Use foam and breathing apparatus. Avoid breathing products of combustion.

Hazard: The coloured square at the top of page 1 is provided for a quick reference as to the hazard level of a product. Blue refers to coatings with low hazard (eg water based wall paints). Yellow refers to medium hazard products such as QD enamels, which contain solvents, are flammable and need respirators for vapour protection. Red refers to products with special hazards such as isocyanate cured two pack finishes